

# Bitu-Mend<sup>®</sup> Pour & Restore

Pour on repairs for worn and damaged asphalt



Watco Bitu-Mend<sup>®</sup> Pour & Restore is ideal for shallow repairs to damaged or cracked asphalt and tarmac. Just mix and pour over pitted, cracked and damaged surfaces and it self smooths with just a little help from a trowel. The kit contains granite aggregate which is sprinkled over the repair to provide a slip resistant surface which blends in with the surrounding area.



**Areas of use:**

- Repairing shallow depressions, dished or pitted asphalt surfaces
- Car parks, yards, pavements

**Features:**

- Easy to mix and apply
- Ideal for shallow repairs
- Ready for traffic in 16 hours

## Need help? Speak to the experts

Our dedicated and professional team are here to help you get the best results for your project. They will talk you through the preparation and application stages when using **Bitu-Mend<sup>®</sup> Pour and Restore**.

Call our expert team on: **01483 418 418** (Weekdays 8:00am - 5:30pm. Saturday 9:00am - 12:00pm)



# Bitu-Mend<sup>®</sup>

## Pour & Restore

Pour on repairs for worn and damaged asphalt

### 1 Surface Preparation

Ensure the void to be filled is clean and dry (slight damp is acceptable).

### 2 Mixing

Pour the tins of Curing Agent and Accelerator onto the Resin and aggregate mix in the outer bucket.

**Please note** – If you are repairing a number of small areas and need to extend the working life of the mixed product, or if the temperature is above 23°C, DO NOT USE the Accelerator. Use a wide bladed tool to ensure thorough mixing.

### 3 Application

Pour the mixed product onto the damaged asphalt and spread out using a trowel. The product will self-smooth to a level finish. Before the Bitu-Mend Pour & Restore cures, sprinkle the finishing aggregate over the repair.

### 4 Safety

All product labels provide general safety information. Material Safety Data Sheets are available. Food products must be removed from the area during application and cure.

### 5 Ordering

Available direct from Watco UK Limited and through agents worldwide. All Watco products are sold subject to the Company's Standard Conditions of Sale.

The Company and its representatives are often asked to comment on potential uses of Watco products which differ from those described in the Company's data sheets. Whilst in such cases the Company and its representatives will always try to offer helpful and constructive advice, the Company cannot be held responsible for the results of such uses unless they are specifically confirmed in writing by Watco.

# Bitu-Mend<sup>®</sup>

## Pour & Restore

Pour on repairs for worn and damaged asphalt

### Specification

<b>Composition</b>	A blend of graded granite aggregate and epoxy resin.
<b>Finish</b>	Granular, black, slip resistant surface.
<b>Number of Components</b>	1 x resin and aggregate mix, 1 x curing agent, 1 x accelerator, finishing aggregate.
<b>Usage Interior/Exterior</b>	Exterior & interior.
<b>Application Tools</b>	Trowel.
<b>Suitable For</b>	Asphalt, tarmac.
<b>Pack Size</b>	15kg
<b>Coverage</b>	1m <sup>2</sup> at 10mm deep.
<b>Depth</b>	6.5mm - 20mm. For deeper repairs see Watco Bitu-Mend <sup>®</sup> or Watco Bitu-Mend <sup>®</sup> Deep Fill.
<b>Chemical Resistance</b>	Good general resistance to many common such as diesel, petrol, etc. Please contact us for advice regarding other chemicals.
<b>Curing Time</b>	Touch dry in 1 hour at 20°C - 25°C, ready for traffic in 16 hours at 20°C - 25°C.
<b>Pot Life</b>	Working life of mixed components: Approximately 15 minutes at 20°C, less in higher temperatures.
<b>Shelf Life</b>	24 months in unopened container.
<b>Storage</b>	Store above 10°C. Do not allow to freeze.