



Crete HF 130

High-build PU concrete mortar

Colour	Availability	
	Quantity per pallet	
	Size / Quantity	34,1 kg 68,2 kg
	Type of container	Set in carton Set in carton
	Container code	34 68
	Art. no.	
	6861	■ ■
Note:		
For each of the two set articles, please order Crete Color Paste separately under its own article number! (red: 685184, green: 685284, beige: 685384, ochre: 685484, grey: 685584)		
34,6 kg unit: 1 x 686134 + 0.5 kg Crete Color Paste		
69.2 kg unit: 1 x 686168 + 2 x 0.5 kg Crete Color Paste		

Application rate See application examples

Range of use ■ Mortar in systems subjected to high chemical and thermal stresses

Property profile ■ High chemical resistance
 ■ High mechanical resistance
 ■ Water vapour diffusion capable
 ■ Thermal resistance up to 130 °C


Characteristic data of the product Density (20 °C) 2.04 g/cm³ (4-component mixture)
 The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Possible system products > [Crete TF 60 \(226867\)](#)

Preparation ■ Substrate requirements
 Only concrete screeds and bonded screeds primed with Crete TF 60 or Crete FP are permitted substrates. The substrate must be load-bearing, dimensionally stable, solid, free of loose parts, dust, oils, grease, rubber marks and any other substances that could interfere with adhesion. It must be primed so as to remove all surface pores. The tensile strength of the surface of the substrate must be at least 1.5 N/mm² on average (smallest individual value of at least 1.0 N/mm²), and the compressive strength must be at least 25 N/mm².

Concrete	max. 6 m% moisture
Cement screed	max. 6 m% moisture

Production of the mixture ■ Mixing
 Add all of the colour paste (component D) to component A.
 Add all of the hardener (component B) to the base compound (components A and D).
 Mix thoroughly with a slow-speed electric mixer (approx. 300 - 400 rpm).
 Insufficient mixing is indicated by streaks forming.
 When the mixture is ready, pour it into into a compulsory mixer using a side scraper shovel.
 Add component C immediately **while stirring** and mix the compound for 3 minutes.
 The mixing times must be strictly observed (timer).



Mixing ratio 2.5 : 2.6 : 29 : 0.5 parts by weight

Directly after production of the mixture, pour onto the prepared surface and spread using suitable tools.



Directions

For professional users only!



- **Conditions for use**
Temperature of the air and substrate: min. +10 °C to max. +20 °C.
Temperature of the material: +15 to +20 °C.
After application, protect the surface for at least 48 hours from exposure to water and moisture.
Relative humidity should not exceed 80%.
The temperature of the substrate must be at least 3 °C above the dew point temperature during application and curing.
 - **Working time (+20 °C)**
max. 10 minutes (including smoothing)
- As a general principle, higher temperatures will reduce and lower temperatures will increase the times stated.

Application examples

- **Synthetic resin mortar**
Using a suitable gauge rake, immediately distribute the material evenly. Then, without waiting, use a trowel or scraper to level off the material again.

Application rate	18 - 24 kg/m ²
------------------	---------------------------

Notes

Unless otherwise specified, all of the values and application rates given above have been determined under laboratory conditions (20 °C) using standard colours. Slight deviations from these values may arise if the product is worked with on site.

When coating continuous surfaces, only use materials with the same batch number as slight differences in colour, gloss and texture may occur.

To delimit the coated surface, sufficient anchoring cuts must be made (width and depth of the cuts is twice the thickness of the coating system).

When levelling off the material, make sure that a pore-free surface is produced.

The resulting surface texture is strongly influenced by the conditions on site and the application method. Therefore, surface texture is not covered by product liability.

PU concretes in general are functional floor coverings with low requirements with regard to appearance and are generally not colour-fast.

Even if the flooring is correctly installed, differences in colour, marks made during application, streaking and slight formation of pools cannot be excluded.

Due to the short reaction time, the coating operation must be well planned and prepared.

Low thickness and low temperature can affect the visual effect of the finished surface.

Abrasive mechanical loads leave traces of wear.

Suitable for vehicle traffic with rubber tyres; not suitable for vehicle loads with metal or polyamide tyres nor for dynamic point loads.

In case of repairs on the surface or working up to existing surfaces, there will be a visible transition in appearance and texture.

The resistance to chemical substances must be assessed with regard to the temperature of the medium (see chemical resistance list).

Further notes on working, system construction and maintenance of the listed products can be found in the latest Technical Data Sheets and the Remmers system recommendations.

Tools / Cleaning


Gauge rake, trowel, scraper, mixer, compulsory mixer if necessary



More detailed information can be found in the Remmers Tool Programme.
Clean tools, equipment and splashed material immediately while fresh with V 101 Thinner.
Take suitable protective and waste disposal measures when cleaning.

Storage / Shelf life

If stored in unopened original containers, in a cool, dry place protected from frost: at least 12 months for components B and D, and at least 6 months for components C and A.



Safety data / Regulations

For professional users only!
Further information concerning safety during transport, storage and handling as well as on disposal and ecology can be found in the latest Safety Data Sheet.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.



VOC content as per the
"Decopaint" Directive
(2004/42/EC)

EU limit value for the product (cat A/j): max. 140 g/l (2010).
This product contains < 140 g/l VOC.

VOC	
Kat.	A/j
2010:	140g/l
max.:	140g/l

Declaration of performance

> [Declaration of performance \(EN\)](#)

Declaration of conformity



Remmers GmbH

Bernhard-Remmers-Str. 13, D – 49624 Lönningen

UKCA Remmers (UK) Limited

Unit 4, Lloyds Court, Manor Royal Crawley, RH10 9QU

CE 19 / UKCA 21

GBIII 143_2

EN 13813:2002

226861

Synthetic resin screed for use internally in buildings

Reaction to fire:	E _{fl}
Release of corrosive substances:	SR
Wear resistance:	≤ AR 0.5
Bond strength:	≥ B 1.5
Impact resistance:	≥ IR 4

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.