



Epoxy MT 100

Fast primer for for slightly moist substrates

Availability				
Quantity per pallet	168	120		
Packaging unit	1 kg	2,5 kg	10 kg	25 kg
Type of container			Tin bucket	Tin bucket
Container code	01	03	11	26
Art. no.				
Epoxy MT 100	0936		■	■
Epoxy MT 100	6362	■	■	

Application rate See application examples

- Range of use**
- Primer, bonding layer, levelling layer for substrates with residual moisture
 - Producing compression-resistant mortars, flow coatings
 - Base layer for blinded covers

- Property profile**
- Substrate-tolerant up to 6 % residual moisture (CM method)
 - Good adhesion on weakly absorbent substrates
 - Fast curing / can be coated after a short time
 - Full cure from +5 °C
 - Can be subjected to mechanical loads
 - Can be subjected to chemical loads
 - Free from plasticisers and nonylphenols
 - Physiologically harmless once fully cured
 - Suitable for use as primer without broadcasting underneath Remmers PU and EU coatings

Characteristic data of the product

On delivery	Component A	Component B	Mixture
Density (20 °C)	1.16 g/cm ³	0.97 g/cm ³	1.08 g/cm ³
Viscosity (25 °C)	950 mPa s	200 mPa s	750 mPa s

■ **Once fully cured**

Flexural tensile strength	approx. 20 N/mm ² *
Compressive strength	approx. 60 N/mm ² *

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Certificates > **Brandprüfung**



- Emissionsprüfung
- Physiologische Unbedenklichkeit

Preparation

■ Substrate requirements

The substrate must be firm, dimensionally stable, capable of bearing loads and free of loose constituents, dust, oil, grease, rubber marks and other substances that could interfere with adhesion.

The tensile strength of the surface of the substrate must be at least 1.5 N/mm² on average (smallest individual value of at least 1.0 N/mm²), and the compressive strength must be at least 25 N/mm².

The substrate can be slightly moist but without liquid film on the surface and should not be exposed to major temperature swings (vapour pressure). In this case the primer must always be applied twice.

Concrete	max. 6 m% humidity
----------	--------------------

Cement screed	max. 6 m% humidity
---------------	--------------------

The substrate must be protected from exposure to moisture from underneath during utilisation.

Weakly absorbing substrates must be tested with regard to their suitability for coating, if necessary a trial surface must be set up.


If the product is used on green concrete (water-cement ratio < 0,45) the substrate must be suitable for blasting or grinding.

■ Substrate preparation

Prepare the substrate by suitable means, e.g. steel ball jetting or diamond grinding, so that it meets the requirements specified above.

Broken out or missing areas in the substrate should be filled flush with the surface using Remmers PCC systems or Remmers EP mortars.

Production of the mixture



■ Multi-chamber bag

Open the outer packaging along the perforation and remove the transparent multi-chamber bag. Remove the dividing strip on the bag. Then mix the two components together by kneading the contents of the bag intensively (approx. 60 seconds).

■ Combi-container

Add the entire quantity of the hardener (component B) to the basic compound (component A).

Mix thoroughly with a slow-speed electric mixer (approx. 300 - 400 rpm).

Pour the mixture into a separate container and mix again thoroughly.

Mix for at least 3 minutes.

Insufficient mixing is indicated by streaks forming.

Mixing ratio (A : B)	71 : 29 parts by weight
----------------------	-------------------------

In the case of filled systems, slowly stir the corresponding quantity of filler into the reaction resin mixture and mix thoroughly.

As soon as the mixture is ready to use, apply it in full to the prepared surface and spread it using suitable tools.



Directions

For professional users only!



■ **Conditions for use**

Temperature of material, surroundings and substrate: min. +5 °C - max. +25 °C.
 During the curing process, the applied material should be protected from moisture which could impair the surface and impair the adhesion.
 Relative humidity should not exceed 80%.
 The temperature of the substrate must be at least 3 °C above the dew point temperature during application and curing.

■ **Working time (+20 °C)**

Approx. 25 minutes

■ **Waiting time (+20 °C)**

Waiting times between working operations: min. 6 hours and max. 24 hours.
 If waiting times are longer due to site conditions, the surface of the previous working operation must be broadcast in a specific manner with fire-dried quartz sand (e.g. grain size 0.3-0.8 mm) while fresh or sanded back until stress-whitening begins to occur before proceeding to the next step.

■ **Drying time (+20 °C)**

Foot traffic after 8hours, mechanical loads after 2 days and full loading capacity after 5 days.

As a general principle, higher temperatures will reduce and lower temperatures will increase the times stated.

Application examples

■ **Impregnation/strengthening**

The mixed resin is diluted with up to 20% by mass of Remmers V 101 Thinner and applied to the surface until saturation, using a suitable tool, e.g. rubber blade, and then worked into the substrate with an epoxy roller.
 It may be necessary to apply several layers.

Application rate	Approx. 0.30 - 0.50 kg/m ² of binder (depending on the substrate)
------------------	--

■ **Priming**

The mixed resin is generously applied to the surface. Distribute with a suitable tool, e.g. rubber blade, and work into the substrate with an epoxy roller so that pores in the surface of the substrate are completely filled.
 It may be necessary to apply several layers.

Application rate	Approx. 0.30 - 0.50 kg/m ² of binder (depending on the substrate)
------------------	--

■ **Levelling layer/scratch coat**

The filled material (up to 1 : 1 parts by weight) is applied to the primed surface and distributed with a suitable trowel. If necessary, work over with a spiked roller.

Application rate	Per mm thickness of the base layer: approx. 0.85 kg/m ² of binder and 0.85 kg/m ² of Selectmix 01/03
------------------	--



■ Synthetic resin mortar

The filled material (up to 1 : 10 parts by weight) is distributed with a smoothing trowel and smoothed.

Application rate	Per mm thickness : approx. 0.2 kg/m ² of binder and 2.0 kg/m ² of Selectmix 25
------------------	--

■ Base layer for blinded coatings

The filled material (up to 1 : 1 parts by weight) is applied to the primed surface and distributed with a suitable toothed trowel or toothed rubber blade. If necessary, work over with a spiked roller.

Fire-dried quartz sand is then broadcast liberally over the base layer while it is still fresh. Remove any loose, surplus sand after hardening.

Application rate	Per mm thickness of the base layer: approx. 0.85 kg/m ² of binder and 0.85 kg/m ² of Selectmix 01/03
------------------	--

Notes

Unless otherwise specified, all of the values and application rates given above have been determined under laboratory conditions (20 °C). Slight deviations from these values may arise if the product is worked with on site.

Primers must always be applied so that all pores are filled; it may therefore be necessary to increase the application rate or to apply a second coat.

As mineral substrates have different absorption capacities, impregnated surfaces have a spotted appearance. Not suitable for high-visibility surfaces.

When coating continuous surfaces, only use materials with the same batch number as slight differences in colour, gloss and texture may occur.

Abrasive mechanical loads leave traces of wear.

Epoxy resins are generally not colourfast when exposed to UV light or weather.

Further notes on working, system construction and maintenance of the listed products can be found in the latest Technical Data Sheets and the Remmers system recommendations.

Tools / Cleaning




Smoothing trowel, toothed trowel, toothed squeegee, epoxy roller, spiked roller, mixing equipment, if necessary a positive mixer

More detailed information can be found in the Remmers Tool Programme.

Clean tools, equipment and splashed material immediately while fresh with V 101 Thinner. Take suitable protective and waste disposal measures when cleaning.

Storage / Shelf life



If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 24 months.

Safety data / Regulations

For professional users only!

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet and the brochure entitled "Epoxy Resins in the Construction Industry and the Environment", issued by Deutsche Bauchemie e.V. (2nd edition 2009).

Personal protective equipment

This information can be obtained from the current Safety Data Sheets and/or the relevant professional associations.



VOC content as per the "Decopaint" Directive (2004/42/EC)

EU limit value for the product (cat. A/j): 500 g/l (2010)
This product contains < 500 g/l VOC.

CE marking



Remmers GmbH

Bernhard-Remmers-Str. 13, D – 49624 Lönningen

10

GBIII 002_4

EN 13813:2002

0936

Synthetic resin screed / synthetic resin coating for use indoors

Reaction to fire:	E _{fl}
Release of corrosive substances:	SR
Wear resistance:	≤ AR 1
Bond strength:	≥ B 1,5
Impact resistance:	≥ IR 4

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.